

HumiSeal 1B12LU - Acrylic Conformal Coating Technical Data Sheet

System Description

A low viscosity, fast air drying, single component, general purpose conformal coating for printed circuit assemblies. Particularly suited for impregnating coil and for coating ferrite cores. Can be soldered through easily or chemically removed. Contains an optical brightener to facilitate inspection under UV light.

Properties of Liquid Humiseal

Density	7.0 ± 0.02 g/cm ³
Solids Content	20 ± 3%
Viscosity range	40cps max.
Flashpoint Fed-Std-141, Meth.4287	-1 ⁰ C
Drying Time to Handle per Fed-Std-141, Meth.4061	10 minutes
Recommended Curing Conditions	24 hrs. @RT or 30mins @ 76°C (65-85%RH)
Time Required to Reach Optimum Properties	7 Days
Thinner Needed (dipping, brushing)	Thinner 503
Thinner Needed (spraying)	Thinner 521
Pot Life at room temperature	12 months
Shelf life at room temperature	12 months

Properties of Cured Humiseal

Thermal Properties

Continuous Use Operating Range	-65 °C to +125 °C
Thermal Shock, MIL-I-46058C	Passes
Solderability	Good
Coefficient of Thermal Expansion - DMA	56ppm/ ⁰ C
Glass Transition Temperature - TMA	32 ⁰ C
Young's Modulus - DMA	1400psi

Physical Properties

Clarity	Transparent
Build per Dip, per ASTM, Meth. D823	0.5mm
Flexibility, per MIL-I-46058C	Very Good
Weather Resistance	Very Good

Electrical Properties

Dielectric Withstand Voltage, volts per MIL-I-46058C	>1500
Dielectric Breakdown Voltage, volts, per ASTM, Meth. D149	6000
Dielectric Constant, at 1MHz and 25 ⁰ C, per ASTM-D150-65T	2.8
Dissipation Factor, at 1MHz and 25 ⁰ C, per ASTM-D150-65T	0.01
Insulation Resistance, ohms, per MIL-I-46058C	250 x 10 ¹²
Moisture Resistance, ohms, per MIL-I-46058C	30 x 10 ⁹

Chemical Properties

Main Constituents	Acrylic
Fungus Resistance, per ASTM-G21	Passes
Resistance to Chemicals	Fair

Values are not intended for use in preparation of specifications.



Application Instructions

Cleanliness of the substrate is of extreme importance for the successful application of a conformal coating. Surfaces must be free of moisture, dirt, wax, grease and all other contaminants. Contamination under the coating will cause problems, which may lead to assembly failures.

HumiSeal coatings may be applied by brush, dip or spray.

Dipping

Depending on the complexity, density and configuration of components on the assembly, it may be necessary to reduce the viscosity of HumiSeal 1B12LU with HumiSeal Thinner 503 in order to obtain a uniform film. Once optimum viscosity is determined, a controlled rate of immersion and withdrawal (2 to 6" per minute) will further insure even deposition of the coating and ultimately a uniform film. During the application, evaporation of solvent causes an increase in viscosity, which should be adjusted by adding small amounts of Thinner 503. Viscosity in the dip tank should be regularly checked by the use of a simple measuring device such as a Zahn or Ford viscosity cup.

Spraying

HumiSeal 1B12LU can be sprayed using conventional spraying equipment. As a rule, the addition of Thinner 521 is necessary to assure a uniform spray pattern resulting in pinhole free film. The amount of thinner and spray pressure will depend on the specific type of spray equipment used. The spraying should be done under an exhaust hood so that the vapour and mist are carried away from the operator. The recommended ratio of HumiSeal 1B12LU to HumiSeal Thinner 521 is 1 to 1 by volume, as a starting point. The quantities may be adjusted to obtain a uniform coating.

Brushing

HumiSeal 1B12LU may be brushed with a small addition of HumiSeal Thinner 503. Uniformity of the film depends on component density and operator's technique.

Storage

HumiSeal 1B12LU should be stored at room temperature, away from excessive heat, in tightly closed containers. HumiSeal products may be stored at temperatures of +5C to +25C. Avoid direct sunlight. Prior to use, allow the product to equilibrate for 24 hours at room temperature.

CAUTION

The solvents in 1B12LU are flammable. Do not use in presence of open flame or sparks. Avoid inhalation of vapours or spray. Use only in well-ventilated areas. Avoid contact with skin and eyes. If contact occurs, wash with soap and water. If swallowed, call physician immediately. Refer to MSDS before use.

Technical support coatings: Europetechsupport@chasecorp.com

Sales: Europeansales@chasecorp.com



Humiseal Europe
Albany Park, Frimley Road,
Camberley, Surrey,
GU16 7PH
Phone +44 (0) 1276 691100
Fax +44 (0) 1276 691227
Web: www.humiseal.com

All technical data in this bulletin is based on test results and is believed to be correct. However, since the end use of HumiSeal materials (and the manner of storing and handling them) is beyond our control, we make no warranty-expressed or implied as to the fitness of use, results to be obtained from or effects of use with respect to these materials. Their use shall be solely by the judgment of and at the risk of the user notwithstanding any statement in this bulletin

© CHASE CORPORATION 1992

